

QUALITY MANAGEMENT ISO 9001

Code: TD_EGGER_SILENZIO_EASY_SD_EN

Revision: 03

Date: 18.11.2020

Technical data sheet

EGGER Silenzio EASY SD

Application area

Underlay material for floating flooring installation of laminate flooring elements (EN 13329/ EN 15468)

Standard data

Product	Silenzio EASY SD		
Material	HFPS-Foam + vapour control layer		
Colour	Green/ silver		
Type of delivery	Folding panel		
Packaging	15 m²/ package 21 packages/ pallet		
Accreditations/ Certificates/ Declarations	Building Inspectorate Approval, TÜV toxproof, A+ (Èmissionsdans l'air intérieur)		

Material data

Parameter	Specification	Tolerance	Test method
Thickness [mm]	2	± 15 %	CEN TS 16354
Length [m]	12.5	+ 5 %/ - 0 %	CEN TS 16354
Width [m]	1.2	+ 2.5 %/ - 1 %	CEN TS 16354
Reaction to fire	Efl	-	EN 13501
Thermoforming [°C]	≤ 70	-	SWN
Water absorption [%]	≤ 1	-	EN 12087
Thermal resistance Rλ [m²K/W]	~ 0,057	-	EN 12667
Water vapor diffusion resistance SD [m]	≥ 100	-	CEN TS 16354

Technical data concerning CEN TS 16354

Description	Parameter	Value	Recommendations according to the EPLF
Impact Sound Reduction	IS [dB]	≤ 18	≥ 18
Reflected Walking Sound Reduction	RWS	27 % according to IHD –W431	in progress
Resistance to Large Ball	RLB [mm]	≥ 1200	≥ 1200
Compressive Strength	CS [kPa]	≥ 110	≥ 60
Compressive Creep	CC [kPa]	≥ 25	≥ 20
Dynamic Load	DL [cycles]	≥ 250000	≥ 100000
Punctual Conformability	PC [mm]	≤1	≥ 0.5

Responsibility: Product Management EGGER Flooring Products, www.egger.com

MORE FROM WOOD.



Logistic parameters

Description	Parameter	Value
Specifications package	Quantity	1
	m²	15
	Dimensions [mm]	1250 x 250 x 95
	Weight [kg]	1,20 +/- 10 %
Specifications pallet	Quantity	21
	m²	315
	Dimensions [mm]	1280 x 800 x 820
	Weight [kg]	70 +/- 10 %

Information

All above mentioned values were determined under laboratory conditions and defined laboratory materials and structures and may with different system flooring components deviate from these test values. For all of the mentioned performance values inaccuracies are possible owing to the testing methods.

The information given above is based on our current state of knowledge and should be used for information of our product application. This should not be taken to as an assurance of certain quality of our products or their use for specific purposes. Subject to change, legal obligations cannot be derived from the information in this document. Existing commercial protective rights are to be observed.

A note on validity

This technical data sheet has been carefully drawn up to the best of our knowledge. It is intended for information only and does not constitute a guarantee in terms of product properties or suitability for specific applications. We accept no liability for any mistakes, errors in standards, or printing errors. In addition, technical changes may result from the further development of EGGER accessories as well as changes to standards and public law documents. This technical data sheet is not an instruction for use and is not a legally binding document