
























TECHNICAL CHARACTERISTICS

wineo 800

Covering type according to EN ISO 10582: Heterogeneous resilient-flooring to glue

wineo

	wineo 800 wood	wineo 800 wood XL	wineo 800 stone XL	wineo 800 tile L / XL / XXL	wineo 800 craft	
Format	1200 x 180 mm	1505 x 235 mm	914.4 x 457.2 mm	457.2 x 457.2 mm 914.4 x 457.2 mm 914.4 x 914.4 mm	457.2 x 457.2 mm 914.4 x 101.6 mm	
Product thickness	2.5 mm	2.5 mm	2.5 mm	2.5 mm	2.5 mm	
Planks, tiles / m² per box	16 / 3.46 m ²	12 / 4.37 m ²	10 / 4.18 m ²	16 / 3.34 m ² 10 / 4.18 m ² 6 / 5.02 m ²	16 / 3.34 m ² 20 / 1.86 m ²	
Boxes / m² per pallet	75 / 259.20 m ²	60 / 262.26 m ²	40 / 167.20 m ²	52 / 173.68 m ² 40 / 167.20 m ² 37 / 185.74 m ²	52 / 173.68 m ² 135 / 250.83 m ²	
Guarantee	25 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de					
Classification						Product composition
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices		1	Surface sealing	
	Utilization class 33 Heavy-duty use in the commercial sector EN ISO 10874	Department stores, lobby's, schools, open plan offices, corridors		2	Surface texture Various embossings	
	Utilization class 42 Normal use in the light industrial sector EN ISO 10874	Storage rooms, workshops		3	Wear layer Thickness 0.55 mm	
	Wear resistance corresponding to the binder content – EN ISO 10582	Type I		4	Decor Decor film	
	Wear resistance EN 660-2	Group T		5	Base layer	
	Reaction to fire EN 13501-1	B _{fl} - s1		6	Backing	
	Anti slip category DIN 51130	R 9		DESIGN FLOORING to glue 		
	Slip resistance EN 13893	μ ≥ 0.30 - DS		wood – bevelled edge tile – bevelled edge		
	Anti-static properties EN 1815	≤ 2 kV		Certifications		
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		 windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf - 07 - Elastischer Bodenbelag DOP: 0401001 EN 14041:2004  Resilient Flooring to be used within a building.		
	Light fastness EN ISO 105-B02	≥ 6		 <p>ÉMISSIONS DANS L'AIR INTÉRIEUR</p> <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p>		
	Residual indentation EN ISO 24343-1	~ 0.02 mm				
	Castor chair test EN 425 / ISO 4918	Type W – no visible change				
	Thermal resistance EN 12667	~ 0.01 (m ² K)/W				
	Impact sound reduction EN ISO 16251-1	~ 4 dB				
	Dimension stability EN ISO 23999	~ 0.15 %				
Disposal	<u>Private:</u> Possible with normal domestic refuse		<u>Commercial:</u> Refuse-key-no. AVV 170203			

Relevant information:

- R 9 Decor „Heavy Metal“ excluded.
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Residual indentation in combination with silentPREMIUM: see separate data sheet silentPREMIUM.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.